

ALSAN® RS

260 LO FLASH

ALSAN® RS 260 LO FLASH
 PRODUCT #
 L-RS052S (pebble grey)
 L-RS054S (traffic white)

PRODUCT DATA SHEET

DESCRIPTION & FEATURES

ALSAN RS 260 LO Flash is a high performance, low odor, rapid-setting, polymethacrylate (PMA) liquid resin for use in flashing applications. ALSAN RS 260 LO Flash is catalyzed with ALSAN RS catalyst powder and combined with ALSAN RS Fleece reinforcing fabric to form a flexible, monolithic, reinforced membrane.

STORAGE

Always store closed containers in cool, ventilated and dry location away from heat and oxidizing agent. Do not store in direct sunlight or in temperatures below 32°F (0°C) or above 77°F (25°C). Approximate shelf life is twelve months from date of manufacture when properly stored, sealed and unmixed.

APPLICATION

Apply ALSAN RS 260 LO Flash with a brush or roller. Prior to application, refer to published specifications and approved details for complete application instructions. The applicator is responsible for ensuring conditions are appropriate to proceed with proper application method.



APPLICATION



BRUSH



ROLLER

QUICK FACTS

UNIT SIZE (kg)	AMBIENT TEMP (°F)	SUBSTRATE TEMP (°F)	RESIN TEMP (°F)	POT LIFE (min)	RAIN PROOF (min)	NEXT LAYER (hour)	FULLY CURED (hour)
12.5 (9.8 L)	32-95 (0 to 35°C)	32-122 (0 to 50°C)	37-86 (3 to 30°C)	15-20 at 68°F (20°C)	45-60 at 68°F (20°C)	1-2 at 68°F (20°C)	5 at 68°F (20°C)



SOPREMA®

www.soprema.us
 310 Quadral Drive, Wadsworth, Ohio 44281
 Toll Free: (800) 356-3521 | Tel: (330) 334-0066

TECHNICAL INFORMATION & TESTING

APPROXIMATE COVERAGE RATES

SUBSTRATE PROFILE	MINIMUM TOTAL CONSUMPTION kg/ft ² (kg/m ²)	BASE COMPONENT CONSUMPTION kg/ft ² (kg/m ²)	TOP COAT CONSUMPTION kg/ft ² (kg/m ²)	TOTAL THICKNESS mils(mm)	BASE COAT mils (mm)	TOP COAT mils (mm)
Smooth	0.28 (3.0)	0.19 (2.0)	0.01 (1.0)	98 (2.5)	65 (1.6)	32 (0.8)
Typical	0.31 (3.3)	0.21 (2.3)		107 (2.7)	74 (1.9)	
Granulated	0.36 (3.8)	0.26 (2.8)		124 (3.1)	90 (2.3)	
Rough	0.40 (4.3)	0.30 (3.3)		140 (3.5)	108 (2.7)	

CATALYST MIXING CHART

CATALYST REQUIRED	SUMMER FORMULATION						WINTER FORMULATION					
	6% Catalyst 37°F (3°C) to 50°F (10°C)		4% Catalyst 50°F (10°C) to 68°F (20°C)		2% Catalyst 68°F (20°C) to 95°F (35°C)		6% Catalyst 32°F (°C) to 37°F (3°C)		4% Catalyst 37°F (3°C) to 50°F (10°C)		2% Catalyst 50°F (10°C) to 68°F (20°C)	
12 kg can	7 0.1 kg packets		5 0.1 kg packets		2.5 0.1 kg packets		7 0.1 kg packets		5 0.1 kg packets		2.5 0.1 kg packets	
1 kg	TBSP	kg	TBSP	kg	TBSP	kg	TBSP	kg	TBSP	kg	TBSP	kg
	6	0.06	4	0.04	2	0.02	6	0.06	4	0.04	2	0.02
1 liter (~1.3 kg)	8	0.08	5	0.05	2.5	0.03	8	0.08	5	0.05	2.5	0.03

PHYSICAL PROPERTIES

PROPERTY	MD	XMD	TEST METHOD
Peak load @ 73.4°F (23°C) control, lbf/in (kN/m)	70 (12.3)	60 (10.5)	ASTM D5147
Elongation @ 73.4°F (23°C) control, %	55	75	ASTM D5147
Peak load @ 73.4°F (23°C) post heat aging, lbf/in (kN/m)	80 (14.0)	80 (14.0)	ASTM D5147
Elongation @ 73.4°F (23°C) post heat aging, %	50	65	ASTM D5147
Peak load @ 73.4°F (23°C) post acc. weathering, lbf/in (kN/m)	70 (12.3)	75 (13.1)	ASTM D5147
Elongation @ 73.4°F (23°C) post acc. weathering, %	55	65	ASTM D5147
Peak load @ 0°F (-18°C), lbf/in (kN/m)	175 (30.6)	150 (26.3)	ASTM D5147
Elongation @ 0°F (-18°C), %	60	70	ASTM D5147
Tear resistance, lbf (N)	80 (356)	75 (334)	ASTM D5147
Dimensional stability, %	0.1	0.1	ASTM D5147
Static puncture resistance, lbf (N)	Pass 56 (249)		ASTM D5602
Shore A hardness, durometer	73		ASTM D2240
Water absorption, %	0.7		ASTM D570 (@ 212°F)
Water vapor permeance, perms	0.2		ASTM E96
Low temperature flexibility, °F (°C)	Pass -33 (-36.1)	Pass - 33 (-36.1)	ASTM D7264
Low temperature crack bridging	No cracks		ASTM C1305
Self-ignition, °F (°C)	770 (410)		ASTM D1929
Smoke density index	300		ASTM E84
Rate of burning, in/min (m/hr)	0.8 (1.2)		ASTM C635

TECHNICAL INFORMATION & TESTING



FLORIDA BUILDING CODE