

## PRODUCT DATA SHEET

### DESCRIPTION & FEATURES

COLPLY Adhesive is a high quality, single component, asphalt cutback adhesive formulated specifically for adhering SBS-modified bitumen membrane systems. COLPLY Adhesive is blended with specially selected and processed asphalt and performance additives with contribute to its smooth troweling consistency.

### STORAGE

Store pail on end and maintain in an upright position to prevent damage. Store in a clean dry location and cover as necessary to protect from environmental damage such as extreme cold, heat, or moisture. Monitor varying environmental conditions during storage, handling and application of COLPLY Adhesive.

### APPLICATION

COLPLY Adhesive is applied to approved, compatible substrates using ¼" inch notched neoprene squeegees or trowels. Apply COLPLY Adhesive at 1.5 to 2 gallons per 100 square feet for sand-surfaced interply applications. The application rate over approved absorptive or rough substrate surfaces vary, requiring 2.5 gallons or more per 100 square feet. Specifically, granulated surfaces require 3 to 4 gallons per 100 square feet. When the ambient temperature is below 50°F (10°C), material should be warmed to a temperature of 70°F (24°C) at the time of application. Refer to the SOPREMA SBS Roofing Manual for additional application guidelines.

APPLICATION



COLD ADHESIVE

QUICK FACTS

ASTM STANDARD	CONTAINER (gal)	COVERAGE* (gal/100ft <sup>2</sup> )
D3019	5.0 (18.9 L)	1.5-2.5

\* Coverage rate as reported assumes installation using side and end lap recommendations.

TECHNICAL INFORMATION & TESTING

PRODUCT INFORMATION	
Description	SBS-modified bitumen membrane adhesive
Installation	Spray, brush, roller or squeegee applied
Packaging, gal (L)	
Pail	5 (18.9)
Drum	55 (208.1)
Tote	350 (1324.8)
Application rate, gal/100ft <sup>2</sup> (absorptive surface)	1.5 - 2.0 (2.0 - 2.5)

TESTING & APPROVALS

