

## PRODUCT DATA SHEET

### DESCRIPTION & FEATURES

COLPLY Flashing Cement is high quality, single component viscous cement formulated specifically for adhering SBS-modified bitumen membrane flashing assemblies. COLPLY Flashing Cement is blended with specially selected and processed asphalt and performance additives which contribute to its smooth troweling consistency.

### STORAGE

Store on end and maintain in an upright position to prevent damage. Store in a clean dry location and cover as necessary to protect from environmental damage such as extreme cold, heat, or moisture. Monitor varying environmental conditions during storage, handling and application of COLPLY Flashing Cement.

### APPLICATION

COLPLY Flashing Cement is applied to approved, compatible substrates using ¼" inch notched neoprene squeegees or trowels. Apply COLPLY Flashing Cement at 2-2.5 gallons per 100 square feet for sand-surfaced interply applications. The application rate over approved absorptive or rough substrate surfaces vary, requiring 2.5 gallons or more per 100 square feet. Specifically, granulated surfaces require 4 to 5 gallons per 100 square feet. COLPLY Flashing Cement is applied to both the flashing ply and the substrate prior to placement of the flashing ply. When the ambient temperature is below 50°F (10°C), material should be warmed to a temperature of 70°F (24°C) at the time of application. Refer to the SOPREMA SBS Roofing Manual for additional application guidelines.

#### QUICK FACTS

ASTM STANDARD	CONTAINER (gal)	COVERAGE* (gal/100 ft <sup>2</sup> )
D4586	5.0 (18.9 L)	2.0 - 2.5 interply

\* Coverage rate as reported assumes installation using side and end lap recommendations.

## TECHNICAL INFORMATION & TESTING

PRODUCT INFORMATION	
Description	SBS-modified bitumen flashing adhesive
Installation	Trowel applied
Packaging, gal (L)	5 (18.9)
Application rate, gal/100 ft <sup>2</sup> (absorptive surface)	1.5 - 2.0 (2.0 - 2.5)

## TESTING & APPROVALS

