

SOPRALENE®

180 FR GR

SOPRALENE® 180 FR GR
PRODUCT # 01365 (WH)
05006 (SG)
01323 (ECO3)

PRODUCT DATA SHEET

DESCRIPTION & FEATURES

SOPRALENE 180 FR GR (fire retardant, granulated) is an SBS-modified bitumen cap ply for use in approved multi-ply membrane and flashing assemblies. SOPRALENE 180 FR GR is composed of a proprietary formulation of elastomeric styrene-butadiene-styrene (SBS) polymer modified bitumen and is reinforced with a tough, dimensionally stable non-woven polyester mat. The topside is surfaced with ceramic coated granules and the underside is surfaced with fine mineral aggregate to facilitate cold adhesive and hot asphalt applications.

SOPRALENE 180 FR GR includes the standard white granules. Contact SOPREMA® Customer Service or your sales representative for other granule color options and special order requirements.

STORAGE & HANDLING

Store rolls on end and maintain in an upright position to prevent damage. Store rolls in a clean dry location and cover as necessary to protect rolls from environmental damage such as extreme cold, heat, or moisture. Monitor varying environmental conditions during storage, handling and application of SOPRALENE 180 FR GR.

APPLICATION

Prior to installation, unroll SOPRALENE 180 FR GR onto the roof surface and allow to relax. Place SOPRALENE 180 FR GR in desired position and back roll the product. Apply approved cold adhesive or hot asphalt following manufacturer specifications. SOPRALENE 180 FR GR is then rolled into the cold adhesive or hot asphalt and subsequently broomed in if utilizing hot asphalt or cold adhesives. Refer to the SOPREMA SBS Roofing Installation Guide for additional application guidelines.



APPLICATION



COLD ADHESIVE



HOT ASPHALT

COOL ROOF RATING

PRODUCT	SOLAR REFLECTANCE		THERMAL EMITTANCE		SRI	
SOPRALENE 180 FR GR Standard white granules (WH)	0.26 initial	0.23 3 year	0.87 initial	0.91 3 year	25 initial	23 3 year
SOPRALENE 180 FR GR Highly reflective white granules (SG)	0.66 initial	0.62* 3 year	0.91 initial	0.91* 3 year	81 initial	75 3 year
SOPRALENE 180 FR GR Smog reducing granules (ECO3)	0.10 initial	N/A	0.89 initial**	N/A	6 initial**	N/A

* CRRC Rapid Ratings. Refer to Cool Roof Ratings Council (CRRC).

**Calculated using internal testing

QUICK FACTS

ASTM STANDARD	LENGTH (ft)	WIDTH (in)	COVERAGE* (ft²)	THICKNESS (mils)	ROLL WEIGHT (lb)	ROLLS/ PALLET (pallet weight)
D6164 Type 1, Grade G	32.8 (10.0 m)	39.4 (1.0 m)	97.9 (9.1 m²)	160 (4.0 mm)	117 (53.1 kg)	25 (2,977 lb/ 1,350 kg)

* Coverage rate as reported assumes installation using side and end lap recommendations.



SOPREMA®

www.soprema.us
310 Quadral Drive, Wadsworth, Ohio 44281
Toll Free: (800) 356-3521 | Tel: (330) 334-0066

TECHNICAL INFORMATION & TESTING

SHEET PROPERTIES	
Reinforcement	Non-woven polyester
Elastomeric bitumen	Proprietary blend of bitumen and SBS polymers
Surfacing	Ceramic coated granules
Back surfacing	Sanded
Selvage surface	Sanded
Side lap, in (mm)	3 (76)
End lap, in (mm)	6 (152)

DIMENSIONS & MASS		
PROPERTY		TEST METHOD
Thickness, mils (mm)	160 (4.0)	ASTM D5147
Thickness @ selvage, mils (mm)	130 (3.3)	ASTM D5147
Net mass per unit area, lb/100ft ² (g/m ²)	109 (5322)	ASTM D5147

PHYSICAL PROPERTIES			
PROPERTY	MD	XMD	TEST METHOD
Peak load @ 0°F (-18°C), lbf/in (kN/m)	115 (4.0)	90 (15.8)	ASTM D5147
Elongation at peak load @ 0°F (-18°C), %	35	40	ASTM D5147
Peak load @ 73.4°F (23°C), lbf/in (kN/m)	85 (14.9)	65 (11.4)	ASTM D5147
Elongation at peak load @ 73.4°F (23°C), %	55	60	ASTM D5147
Ultimate elongation @ 73.4°F (23°C), %	65	80	ASTM D5147
Tear strength @ 73.4°F (23°C), lbf (N)	125 (556)	85 (378)	ASTM D5147
Low temperature flexibility, °F (°C)	-15 (-26)	-15 (-26)	ASTM D5147
Dimensional stability, %	< 0.5	< 0.5	ASTM D5147
Compound stability, °F (°C)	240 (116)	240 (116)	ASTM D5147
Granule embedment, g	1.5 avg; 2.0 max for SG		ASTM D5147
Cyclic fatigue, condition 5	Pass		ASTM D5849

* Data is represented by average values, unless noted otherwise.

TESTING & APPROVALS

