

ELASTOPHENE®

SANDED 2.2

ELASTOPHENE®
SANDED 2.2
PRODUCT # 00206

PRODUCT DATA SHEET

DESCRIPTION & FEATURES

ELASTOPHENE Sanded 2.2 is an SBS-modified bitumen base ply for use in approved multi-ply membrane and flashing assemblies. ELASTOPHENE Sanded 2.2 is composed of a proprietary formulation of elastomeric styrene-butadiene-styrene (SBS) polymer modified bitumen and is reinforced with a high quality random glass fiber mat. The topside and underside are surfaced with fine mineral aggregate to facilitate cold adhesive and hot asphalt applications.

STORAGE & HANDLING

Store rolls on end and maintain in an upright position to prevent damage. Store rolls in a clean dry location and cover as necessary to protect rolls from environmental damage such as extreme cold, heat, or moisture. Monitor varying environmental conditions during storage, handling and application of ELASTOPHENE Sanded 2.2.

APPLICATION

Prior to installation, unroll ELASTOPHENE Sanded 2.2 onto the roof surface and allow to relax. Place ELASTOPHENE Sanded 2.2 in desired position and back roll the product. Apply approved cold adhesive or hot asphalt following manufacturer's guidelines. ELASTOPHENE Sanded 2.2 is then rolled into the cold adhesive or hot asphalt and subsequently rolled with a weighted roller. Subsequent approved inter-ply or cap ply membranes are applied to ELASTOPHENE Sanded 2.2 via cold adhesive or hot asphalt. Refer to the SOPREMA® SBS Roofing Manual for additional application guidelines.



APPLICATION



COLD ADHESIVE HOT ASPHALT

QUICK FACTS

ASTM STANDARD	LENGTH (ft)	WIDTH (in)	COVERAGE* (ft²)	THICKNESS		ROLL WEIGHT (lb)	ROLLS/PALLET (pallet weight)
				MIN	AVERAGE		
D6163 Type 1, Grade S	49.2 (15.0 m)	39.4 (1.0 m)	147.6 (13.7 m²)	87 (2.2 mm)	91 (2.3 mm)	102 (46.3 kg)	30 (3,110 lb/ 1,411 kg)

* Coverage rate as reported assumes installation using side and end lap recommendations.



SOPREMA®

www.soprema.us
310 Quadral Drive, Wadsworth, Ohio 44281
Toll Free: (800) 356-3521 | Tel: (330) 334-0066

TECHNICAL INFORMATION & TESTING

SHEET PROPERTIES	
Reinforcement	Glass fiber
Elastomeric bitumen	Proprietary blend of bitumen and SBS polymers
Top surfacing	Sanded
Back surfacing	Sanded
Selvage width, in (mm)	3 (76)
End lap, in (mm)	6 (152)

DIMENSIONS & MASS		
PROPERTY		TEST METHOD
Thickness, mils (mm)	87 (2.2 mm)	ASTM D5147
Min	91 (2.3 mm)	
Average		
Net mass per unit area, lb/100ft ² (g/m ²)	63 (3074)	ASTM D5147

PHYSICAL PROPERTIES			
PROPERTY	MD	XMD	TEST METHOD
Peak load @ 0°F (-18°C), lbf/in (kN/m)	100 (17.5)	90 (15.8)	ASTM D5147
Elongation at peak load @ 0°F (-18°C), %	4	4	ASTM D5147
Peak load @ 73.4°F (23°C), lbf/in (kN/m)	50 (8.8)	40 (7.0)	ASTM D5147
Elongation at peak load @ 73.4°F (23°C), %	5	4	ASTM D5147
Ultimate elongation @ 73.4°F (23°C), %	45	45	ASTM D5147
Tear strength @ 73.4°F (23°C), lbf (N)	60 (267)	60 (267)	ASTM D5147
Low temperature flexibility, °F (°C)	-15 (-26)	-15 (-26)	ASTM D5147
Dimensional stability, %	< 0.1	< 0.1	ASTM D5147
Compound stability, °F (°C)	250 (121)	250 (121)	ASTM D5147

* Data is represented by average values, unless noted otherwise.

TESTING & APPROVALS



FLORIDA BUILDING CODE

MIAMI-DADE COUNTY
APPROVED

