

# ELASTOPHENE®

## SP 2.2

ELASTOPHENE® SP 2.2  
PRODUCT # 00490

## PRODUCT DATA SHEET

### DESCRIPTION & FEATURES

ELASTOPHENE SP 2.2 (sanded, polyolefin) is an SBS-modified bitumen base ply for use in approved multi-ply membrane and flashing assemblies. ELASTOPHENE SP 2.2 is composed of a proprietary formulation of elastomeric styrene-butadiene-styrene (SBS) polymer modified bitumen and is reinforced with a high quality random glass fiber mat. The topside is surfaced with fine mineral aggregate and underside are surfaced with polyolefin burn-off film to optimize heat welding.

### STORAGE & HANDLING

Store rolls on end and maintain in an upright position to prevent damage. Store rolls in a clean dry location and cover as necessary to protect rolls from environmental damage such as extreme cold, heat, or moisture. Monitor varying environmental conditions during storage, handling and application of ELASTOPHENE SP 2.2.

### APPLICATION

Prior to installation, unroll ELASTOPHENE SP 2.2 onto the roof surface and allow to relax. Position ELASTOPHENE SP 2.2 in desired position and back roll the product. ELASTOPHENE SP 2.2 is then heat welded to approved substrates. Subsequent approved inter-ply or cap ply membranes are applied to ELASTOPHENE SP 2.2 via cold adhesive or hot asphalt. Refer to the SOPREMA® SBS Roofing Manual for additional application guidelines.



APPLICATION



HEAT-WELDED

QUICK FACTS

ASTM STANDARD	LENGTH (ft)	WIDTH (in)	COVERAGE* (ft <sup>2</sup> )	THICKNESS (mils)	ROLL WEIGHT (lb)	ROLLS/PALLET (pallet weight)
D6163 Type 1, Grade S	49.2 (15.0 m)	39.4 (1.0 m)	147.6 (13.7 m <sup>2</sup> )	87 (2.2 mm)	95 (43.1 kg)	30 (1,595 lb/ 723.5 kg)

\* Coverage rate as reported assumes installation using side and end lap recommendations.



**SOPREMA®**

[www.soprema.us](http://www.soprema.us)  
310 Quadral Drive, Wadsworth, Ohio 44281  
Toll Free: (800) 356-3521 | Tel: (330) 334-0066

## TECHNICAL INFORMATION & TESTING

SHEET PROPERTIES	
Reinforcement	Glass fiber
Elastomeric bitumen	Proprietary blend of bitumen and SBS polymers
Top surfacing	Sanded
Back surfacing	Polyolefin film
Selvage width, in (mm)	3 (76)
End lap, in (mm)	6 (152)

DIMENSIONS & MASS		
PROPERTY		TEST METHOD
Thickness, mils (mm)	87 (2.2)	ASTM D5147
Thickness @ selvage, mils (mm)	79 (2.0)	ASTM D5147
Net mass per unit area, lb /100 ft <sup>2</sup> (g/m <sup>2</sup> )	62.6 (3054)	ASTM D5147
Bottom coating thickness, mils (mm)	≥ 40 (1.0)	ASTM D5147

PHYSICAL PROPERTIES			
PROPERTY	MD	XMD	TEST METHOD
Peak load @ 0°F (-18°C), lbf/in (kN/m)	100 (17.5)	90 (17.5)	ASTM D5147
Elongation at peak load @ 0°F (-18°C), %	4	4	ASTM D5147
Peak load @ 73.4°F (23°C), lbf/in (kN/m)	50 (8.8)	40 (7.0)	ASTM D5147
Elongation at peak load @ 73.4°F (23°C), %	5	4	ASTM D5147
Ultimate elongation @ 73.4°F (23°C), %	45	45	ASTM D5147
Tear strength @ 73.4°F (23°C), lbf (N)	60 (267)	60 (267)	ASTM D5147
Low temperature flexibility, °F (°C)	-15 (-26)	-15 (-26)	ASTM D5147
Dimensional stability, %	< 0.1	< 0.1	ASTM D5147
Compound stability, °F (°C)	250 (121)	250 (121)	ASTM D5147

\* Data is represented by average values, unless noted otherwise.

## TESTING & APPROVALS

