

SENTINEL®

P150 HFB

SENTINEL® P150 HFB
PRODUCT #
P304 (White)
P304-T (Tan)
P304-G (Grey)

PRODUCT DATA SHEET

DESCRIPTION & FEATURES

SENTINEL P150 HFB is a high performance, polyester reinforced, thermoplastic polyvinyl chloride (PVC) roof membrane, specially designed to provide unmatched flexibility and long-term performance. SENTINEL membranes provide the proven fire and chemical resistance of PVC along with superior weldability, making it easy to conform to complex geometries. SENTINEL P150 HFB incorporates a heavy fleece-backed underside and is available in an ENERGY STAR® approved white as well as a variety of colors, including gray and tan.

STORAGE

Store rolls in a clean, dry location and cover as necessary to protect rolls from environmental damage such as extreme cold, heat, or moisture. Monitor varying environmental conditions during storage, handling and application of SENTINEL P150 HFB.

APPLICATION

SENTINEL P150 HFB can be installed in mechanically attached or fully adhered systems. For fully adhered systems, SENTINEL H2O bonding adhesive is approved. Please refer to the specific adhesive data sheet for application guidelines. For mechanically attached systems, please consult your SOPREMA representative for specific fastening patterns. All laps must be heat-welded to ensure a water tight seal.

COOL ROOF RATING

PRODUCT	SOLAR REFLECTANCE		THERMAL EMITTANCE		SRI	
SENTINEL P150 HFB White	0.85 initial	0.73 3 year	0.89 initial	0.88 3 year	108 initial	90 3 year
SENTINEL P150 HFB Light Grey	0.46 initial	pending 3 year	0.89 initial	pending 3 year	53 initial	pending 3 year
SENTINEL P150 HFB Light Tan	0.72 initial	pending 3 year	0.85 initial	pending 3 year	88 initial	pending 3 year

APPLICATION



MECHANICALLY FASTENED



FULLY ADHERED

QUICK FACTS

ROLL WIDTH (ft)	ROLL LENGTH (ft)	COVERAGE (ft²)	THICKNESS (mils)	ROLL WEIGHT (lb)	ROLLS/PALLET (pallet weight)
10 (3.0 m)	80 (24.4 m)	800 (74.3 m²)	60 (1.5 mm)	303 (137.4 kg)	10 (3,180 lb/ 1,442 kg)

* Coverage rate as reported assumes installation using side and end lap recommendations.



SOPREMA®

www.soprema.us
310 Quadral Drive, Wadsworth, Ohio 44281
Toll Free: (800) 356-3521 | Tel: (330) 334-0066

TECHNICAL INFORMATION & TESTING

SHEET PROPERTIES	
Reinforcement	Polyester (18X9, weft inserted)
Back surfacing	Heavy fleece-backed (5.5 oz/yd ²)
ASTM standard	ASTM 4434, Type III

DIMENSIONS & MASS		
PROPERTY		TEST METHOD
Thickness, mils (mm) (without fleece backing)	60 (1.5)	ASTM D4434
Thickness over scrim, mils (mm)	30 (0.76)	ASTMD4434
Net mass per unit area, lb/100ft ² (g/m ²)	39 (1,905)	ASTM D4434

PHYSICAL PROPERTIES			
PROPERTY	MD	XMD	TEST METHOD
Breaking strength, lbf/in (kN/m)	475 (83)	325 (57)	ASTM D751
Elongation at break, minimum, %	30	30	ASTM D751
Seam strength (min 75% of breaking strength)	Pass	Pass	ASTM D751
Low temperature bend, @ -40°F (-40°C)	Pass	Pass	ASTM D2136
Tear strength, lbf (N)	145 (645)	85 (378)	ASTM D751, Proc. B
Trapezoidal tear, lbf (N)	160 (172)	130 (578)	ASTM D751
Linear dimensional change, %	< 0.1	< 0.1	ASTM D1204
Change in weight after immersion in water, %	< 3	< 3	ASTM D570
Static puncture resistance, @ ≥ 33 lbf (15 kg), minimum	Pass	Pass	ASTM D5602
Dynamic puncture resistance, @ 10 J, minimum	Pass	Pass	ASTM D5635

* Data is represented by average values, unless noted otherwise.

TESTING & APPROVALS

